

Recent information about an inhibited transformer oil based on Shell GTL technology

Ed van Schaik Shell, Germany







Recent information about an inhibited transformer oil based on Shell GTL technology



RECENT INFORMATION ABOUT AN INHIBITED TRANSFORMER OIL BASED **ON SHELL GTL TECHNOLOGY**

TLM Conference Dubai, October 27-28, 2015



Dr. Joerg Friedel Product Application Specialist

Copyright Shell Global Solutions International B.V.

DEFINITIONS AND CAUTIONARY NOTE

Cautionary Note

The companies in which Royal Dutch Shell plc directly and indirectly owns investments are separate entities. In this document "Shell", "Shell group" and

Cautionary NoteThe companies in which Royal Dutch Shell plc directly and indirectly owns investments are separate entities. In this document "Shell", "Shell group" and "Royal Dutch Shell" are sometimes used for convenience where references are made to Royal Dutch Shell plc and its subsidiaries in general. Likewise, the words "we", "us" and "our" are also used to refer to subsidiaries in general or to those who work for them. These expressions are also used where no useful purpose is served by identifying the paraticular company or companies. "Subsidiaries", "Shell subsidiaries" and "Shell companies" as used in this document feel to companies over which Shell plc either directly or indirectly has control. Companies over which Shell has joint control are referred to as "joint ventures" and companies over which Shell plc either directly and/or indirect ownership interest held by Shell in a venture, partnership or company, after exclusion of all third-party interest. This document contains forward-looking statements concerning the financial condition, results of operations and businesses of Royal Dutch Shell. All statements contentional fer materially free materially free materials proceed on amagement's current expectations and assumptions. These statements. Forward-looking statements of hiotre expectations that are based on management's expections and assumptions. These statements, Forward-looking statements include, among other things, statements concerning the potential exposure of Royal Dutch Shell to market risks and statements expressing management's expectations, beliefs, estimates, forecasts, projections and assumptions. These storements. Forward-looking statements included are store "seetile to the materially from those expressed or implicit in these statements included in this document ("setimate", "sett", "solution, "sett", "oluto, "sett", "oluto, "sett", "should, "respect", "goods," "interd", "many", "objectives", "outlook", "palm," "probably," "project", "risks, "schedule,", "sett, "sett", "settema

We may have used certain terms, such as resources, in this document that the United States Securities and Exchange Commission (SEC) strictly prohibits us from including in our filings with the SEC. U.S. investors are urged to consider closely the disclosure in our Form 20-F, File No 1-32575, available on the SEC website <u>www.sec.gov</u>. You can also obtain this form from the SEC by calling 1-800-SEC-0330. Copyright Shell Global Solutions International B V

S5 2-




Recent information about an inhibited transformer oil based on Shell GTL technology

AGENDA

- GTL-process and use of GTL products
- History of transformer oils
- Diala S4 ZX-I properties
- Diala S4 ZX-I field experiences
- Diala S4 ZX-IG

Copyright Shell Global Solutions International B.V.




Ed van Schaik, Shell



3



Recent information about an inhibited transformer oil based on Shell GTL technology



4→ **S5**



Recent information about an inhibited transformer oil based on Shell GTL technology

DEVELOPMENT OF TRANSFORMER OILS


			Diala S4 ZX-I (GTL + 0,2 % DBPC)
Properties	IEC 60296 spec (7.1)	Diala S4 ZX-I	
BDV	30+ kV	60-75 kV	Reliability
Flashpoint	> 135°C	191°C	Safety
Viscosity -30oC	< 1800 cSt	523 cSt	Fast cold start up
Pourpoint	< - 40°C	- 42°C	Allround applicable
Sulfur %	< 0,05%	Sulfur free	No risk on Cuper / Silver &
Oxidation test (500	hours)		Sulfur corrosion
*Acid nr (TAN)	< 0,3	0,02	
*Deposit / sludge	< 0,05	< 0,01	Very high oxidation resistant
*DDF	< 0,05	0,001	
e La		с I I	

Evolution oil type & performance level in recent decates

opyright Shell Global Solutions International B.V.

SHELL GAS TO LIQUID PROCESS


The Shell GTL process transforms natural gas into liquid and solid hydrocarbons with high purity.







Recent information about an inhibited transformer oil based on Shell GTL technology



EXCEPTIONAL RESISTANCE TO OXIDATION VERSUS LEADING COMPETITOR TECHNOLOGY

IEC 61125C	Metric	Competitor Oil X 670 hours	Competitor Oil X 690 hours	Diala S4 ZX I 690 hours	Diala S4 ZX I 980 hours
Total Acidity	mg KOH/g	1,71	2,15	0,01	1,05
Sludge	m%	0,10	0,14	<0,01	<0,01
DDF	-	0,035	0,035	0,0017	0,0063

Table shows Shell data

- Procedure: Oxidation IEC 61125C samples in parallel testing, volatile acidity is monitored.
- Standard test time in IEC 61125C for inhibited products is 500hours.
- Oil X is an "ultra grade" naphthenic oil.

Copyright Shell Global Solutions International B.V.






Recent information about an inhibited transformer oil based on Shell GTL technology

TYPICAL DATA SHOWS THE PROPERTIES THAT DIFFERENTIATE SHELL DIALA S4 ZX-I

	Unit	Standard	IEC 60296Table 2 + section 7.1	
Density 20 °C	kg/m³	ISO 3675	max. 895	805
kin. Viscosity 40 °C	mm²/s	ISO 3104	max. 12	9,6
kin. Viscosity -30°C	mm²/s	ISO 3104	max. 1800	382
Flashpoint PM	°C	ISO 2719	min. 135	191
Pour Point	°C	ISO 3016	max40	-42
Total Sulphur content	mg/kg	ASTM D 5185	max. 500	< 1
DBPC content	%		0,4	0,2
Volatility 107 °V, 22 h	% m	ASTM D 2007		0,75
Dielectric dissipation factor (DDF) 90 °C		IEC 60247	max. 0,005	< 0,001
Oxidation stability (500h/120 °C)		IEC 61125C		
Total Acidity	mg KOH/g		max. 0,3	0,02
Sludge	% m		max. 0,05	< 0,01
DDF at 90 °C			max. 0,05	0,001

TRANSFORMER OIL REQUIREMENTS



*comparison against naphthenic high grade Diala S3 ZX-I


Copyright Shell Global Solutions International B.V.

12

7**→** S5



Recent information about an inhibited transformer oil based on Shell GTL technology







Recent information about an inhibited transformer oil based on Shell GTL technology

IN MANY WAYS, SHELL DIALA S4 ZX-I REMAINS SIMILAR TO MINERAL BASED TRANSFORMER OILS...

	GtL based transformer oil
Dissolved gas analysis	DGA interpretation can use same tools as for traditional hydrocarbon oils (e.g. with Duval diagram)
Failure Detection	In case of a transformer failure (e.g. due to PD) Hydrogen will be generated, Buchholz relay can release an alarm
Material compatibility	Compatibility given for materials which are compatible with mineral oils - Same substance class as mineral oils (hydrocarbons)
Water solubility	Comparable with naphthenic transformer oils
Compatibility with naphthenic oils	Given (used and unused oils), no issue observed in many tests

© Shell Global Solutions International B.V,; All rights reserved.

POSITIVE EXPERIENCES WITH GTL TRANSFORMER OIL

Since 2013 GtL transformer oil has been used to fill thousands of transformers across three continents, more than 25 Mio litre has been sold.

For applications in

- Distribution transformers
- Power transformers
- Reactors
- Instrument transformers
- Traction transformers
- Good Performance no issues observed, function as expected for an high grade oil
- No design or maintenance changes required (possible optimization and maintenance reduction being explored!)
- Proven to be able to detect failures in transformers by initiating Buchholz relay alarm

Copyright Shell Global Solutions International B.V.

1.4

15





Recent information about an inhibited transformer oil based on Shell GTL technology

PERFORMANCE AFTER ONE YEAR IN SERVICE

New transformers filled with Diala S4 ZX-I -first oil analysis after one year in service

Туре	N2	02	CO2	CO	H2	CH4	C2H2	C2H4	C2H6	C3H6	C3H8	TAN	BDV	DDF	BHT	IFT
380kV-grid transformer (350 MVA)	53423	24974	226	114	2	1	0	0	0	10	0					
380kV-grid transformer (350 MVA)	6849	4262	191	51	0	1	0	0	0	0	0	0	75	0,001	0,21	48
380kV-grid transformer (350 MVA)	3006	1639	74	18	0	0	0	0	0	0	0					
30kV-reactor (50MVA)	62753	31889	429	74	3	0	0	0	0	0	0					
30kV-reactor (50MVA)	38678	15444	178	36	0	1	1	1	1	0	0	0	78	0,0009	0,22	47
30kV-reactor (50MVA)	63935	31640	436	88	3	7	0	12	0	3	0					
30kV-reactor (50MVA)	57350	28661	131	41	4	7	0	8	0	0	0	0	86	0,004		44
30kV-reactor (50MVA)	68358	34739	378	85	4	7	0	0	0	0	0					
30kV-reactor (50MVA)	54609	24606	888	69	7	6	0	2	18	0	0	0	72	0,0002	0,2	46
30kV-reactor (50MVA)	5788	3422	95	42	1	0	0	1	0	0	0	0	86	0,004	0,23	42

Source: Amprion/Siemens

17

© Shell Global Solutions International B.V,; All rights reserved.

PERFORMANCE IN A TRANSFORMER REFILLED WITH DIALA S4 ZX-I

• GTL oil still bright with no signs of sludge after 18 months

Date	CO ₂	со	H ₂	CH ₄	C_2H_2	C ₂ H ₄	C ₂ H ₆	TAN	BDV	DDF	IFT
10 Jul 12	1,178	221	164	3.5	0.01	2.3	1.4	0.06	61	0.207	22.2
23 Oct 12	1,595	126	6.2	5.3	0.01	3.9	3.5	0.06	73	0.264	22.6
30 Jan 13	1,342	100	202	2.4	0.01	2.4	1.9	0.06	60	0.299	
15 May 13	1,153	139	174	2.8	0.01	2.1	1.7	0.06	83	0.121	23.6
04 Jul 13	79	2	3.1	0.6	0.01	0.1	0.1	0.01	88	0.061	37.4
28 Aug 13	182	17	12	1.2	0.01	0.4	0.3	0.01	83	0.021	36.3
11 Dec 13	547	43	89	1.9	0.01	0.6	0.5	0.01	89	0.034	36.4
26 Jan 14	79	2	0.5	1	0.01	0.2	0.1	0.01	78	0.034	32.2
24 Mar 14	169	35	6.1	1.5	0.01	0.3	0.3	0.01	84	0.022	32.2
02 Jul 14	625	75	9.8	2.7	0.01	0.3	0.2	0.01	72	0.022	35.2
25 Nov 14	473	76	1.9	1.8	0.43	0.4	0.4	0.01	66	0.034	33.7
										So	urce: EDF UI

Power plant station unit transformer (10 years old)

Hawker Siddeley (1986), 132 kV, 90 MVA, free breathing. Changed to Shell GTL oil June/July 2013. Vacuum applied January 2014. No issues

© Shell Global Solutions International B.V,; All rights reserved.

18





Recent information about an inhibited transformer oil based on Shell GTL technology

SHELL RECOMMENDATION FOR USE OF SHELL DIALA S4 ZX-I

In the case of a change from Shell Diala S2/Shell Diala S3 to Shell Diala S4 ZX-I

Vacuum Treatment and Filtration	No change to Shell Diala S3
Oil Reclamation	No change to Shell Diala S2/S3
Top up Diala S2/S4	Up to 10 % no objection*
Fill old transformers	15 % remaining oil acceptable*
Oil monitoring	As described in IEC 60422
Interpretation of DGA	As described in IEC 60599
Concentration measurement of Antioxidant	As described in IEC 60666

* Assuming that the oil is not heavily aged

19

Copyright Shell Global Solutions International B.V.

Shell Diala S4 ZX-IG

	Diala S3 ZX- IG	Diala S4 ZX- IG	Diala S4 ZX-I
Density [kg/m³]	886	806	805
V40 [mm ² /s]	8,0	9,4	9,6
Flash Point [°C]	136	158	191
Pourpoint [°C]	-57	-42	-42
Oxidation 500h/120°C TAN [mgKOH/g]	1,0 Limit 0,3*	0,02	0,02
Sludge [m%]	0,45 Limit 0,05*	< 0,05	<0,01
DDF	0,12 Limit 0,05*	0,001	<0,0003
Gassing tendency IEC	-10	-5	30
* High grade limits			

 Fulfils IEC 60296 high grade specification (§ 7.1)

+

 Fulfils ASTM D 3487 type II specification including gassing tendency

© Shell Global Solutions International B.V., 2013. All rights reserved.





Recent information about an inhibited transformer oil based on Shell GTL technology

